



## Acculam<sup>®</sup> Epoxyglas G11 nonFR Product Data Sheet

### **Product Description**

Acculam<sup>®</sup> Epoxyglas G11 nonFR -Laminate sheet comprised of heat resistant/halogen free epoxy resin and a woven fiberglass substrate. It qualifies to NEMA G11 and MIL-I-24768/3

### **Typical Applications**

This material exhibits extremely high mechanical strength at elevated temperatures and has good dielectric loss and electric strength properties under both dry and humid conditions. It is resistant to flow, dimensional change, chemicals and has low moisture absorption.

### **Typical Properties**

#### Physical Data

	<b><u>Typical Value</u></b>	<b><u>Units</u></b>
Specific Gravity/Density	1.85	g/cm <sup>3</sup>
Water Absorption - .125"	< .10	%
Temperature Index	180 \ 356	°C \ °F
Rockwell Hardness	115	M scale
Bond Strength	> 2,200 \ 1,000	lbs \ kgs
Flexural Strength-LW-A	> 75,000 \ 520	PSI \ MPa
Flexural Strength-LW-E-1/150	> 40,000 \ 280	PSI \ MPa
Izod Impact Strength-LW	> 10	ft-lbs/in
Izod Impact Strength-CW	> 8	ft-lbs/in
Compressive Strength-Flatwise	> 65,000 \ 448	PSI \ MPa

#### Electrical Data

Dielectric Breakdown-A	> 50	kV
Dielectric Breakdown-D48/50	> 50	kV
Permittivity-A	4.8	
Permativity-D24/23	4.8	
Dissipation Factor-A	0.017	
Dissipation Factor-D24/23	0.018	

*Accurate provides this data as information only and does not imply any warranty for its use or application.*